# . 2018\_05 • This revision cancels all previous ones. Please, obtain the latest version from our web site • www.grupopuma-dz.com. 828 Zone Industrielle Sidi Bel Abbés - 22000 • T: 00 213 (0) 48 70 34 34 • 00 213 (0) 48 70 35 35 • F: 00 213 (0) 48 70 35 55 • info@grupopuma-dz.com

# **DECORATIVE PLASTERS**



# **MORCEM®** ESTUCO FINO

# **MORCEM® STUCCO THIN**

Colored lime mortar for smooth/trowel finish







### **DESCRIPTION**

Lime mortar for wall covering and decorating. Outdoor and indoor.

### **TECHNICAL CARACTERISTICS**

**ADVANTAGES AND USES** 

- · High adherence.
- · To be applied indoors and outdoors.
- No paints necessary. Excellent façade finishes.
- Environmentally friendly, this product is included in the "Green Line."

### **SUITABLE SUBSTRATES**

• MORCEM THICK STUCCO is a waterproofing solution as it is the most recommended base layer for MORCEM FINE STUCCO, conventional cement based substrates, paints that are in good condition, plaster, and plasterboard.

Aerial lime based product, with balanced grain size distribution aggregates and other additives.

· Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products,

### **APPLICATION PROCEDURE**

- · Add water and mix by hand or mechanically until it takes on an even and workable consistency, and lump-
- · Spread the mixed product.
- The paste is spread using a steel trowel, leaving a thickness between 2 and 4 mm.
- To prepare for MORCEM EXTRA FINE STUCCO go over with steel trowel until a smooth finish is obtained.
- The smooth finish is obtained by troweling the material with a sponge trowel.

### **RECOMMENDATIONS**

- . Do not apply directly on the wall (brick, concrete block, etc) given that the purpose of this material is strictly decorative and must be always applied over MORCEM THICK STUCCO, or roughcast that meets the technical requirements for facade protection.
- Do not apply below 5°C nor above 30°C.
- · Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- It is not advisable to apply on horizontal or sloped surfaces.

### **PACKAGING AND STORAGE**

**TECHNICAL DATA** 

25 kg plastic-lined paper bags. Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.



## **DECORATIVE PLASTERS**

# **MORCEM®** ESTUCO FINO

(Statistical data obtained under standard conditions)	
Aspect	COLOURED powder
Thickness of application	2-4 mm.
Powder density	0,7 g/cm <sup>3</sup>
Density of mass	1,25g/cm³
UNE-EN 998-1 Classification	CR W0
Efficiency	3 Kg/m²
Colours	Check range

### **LEGAL DISCLAIMER**

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.

