



PUMACRIL DECORACIÓN SATINADA PUMACRIL DECORATION GLOSSY

Plastic decorative coating for interiors and exteriors

DESCRIPTION

Product best for interior and exterior decoration.

TECHNICAL CHARACTERISTICS

Coating formulated from aqueous dispersal of vinyl resin, pigments and special additives.

ADVANTAGES AND USES

- Excellent adherence on vertical and interior facing of concrete, plaster and construction material based on cement.
- Great whiteness and opacity.
- Good resistance to ageing and yellowing.
- Excellent washability and resistance to damp rubbing.

SUITABLE SUBSTRATES

NEW SURFACES

- Eliminates dust, grease and other contaminants
- Apply a layer of FIJAMOR diluted with 2 or 3 parts of water to equalise support absorption.
- Apply the paint according to instructions for use

ANCIENT SURFACES

- Eliminate mold pollution with bleach or other appropriate decontaminant, as well as loose paint pieces or other construction material.
- Level irregularities with appropriate putty. Leave to dry and sandpaper.
- Apply a layer of FIJAMOR diluted with 2 or 3 parts of water to equalise support absorption.
- The use of hydrofuge sealer is recommended on surfaces in poor conditions, poorly united or with dampness problems.
- Apply the painture according to instructions for use.

APPLICATION PROCEDURE

- Shake until mixture is homogeneous.
- Dilute the first layer between 10-15% of water.
- The second hand and following hands can be diluted up to a maximum of 5% with water.
- Apply with brush or roller if you intend to achieve greater performance and more decorative results.
- Dry to touch time 30 minutes
- Cleaning of tools done with water immediately after use.

RECOMMENDATIONS

PAINTS

PUMACRIL DECORACIÓN SATINADA

PACKAGING AND STORAGE

- Do not apply at temperatures below 5°C.
- Do not apply either with relative humidity greater than 85% or on wet supports.
- Stores in fresh and dry places.

4 and 15 L tub.

Shelf life: 1 year in sealed original packaging, sheltered from outside conditions and humidity

TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Colour	WHITE
Brightness	SILKY
Viscosity (22°C)	80 dPas +/- 10
Specific weight	1,24 Kg/L
Theoretical efficiency	9 at 11 m²/L
Dry out times	30 min. to tact

Repainting interval	Minimum 3 hours, depending on room temperature
---------------------	--

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.