



MORCEM® THERM PERFIL ÁNGULO PVC CON MALLA

MORCEM® THERM PVC PROFILE WITH MESH

DESCRIPTION

Corner reinforcement profile in perforated PVC, used in the MORCEM® THERM System.

TECHNICAL CHARACTERISTICS

PVC profile with fiberglass mesh with anti-alkaline treatment.

ADVANTAGES AND USES

- Easy to apply.
- Reinforcement of corners in the MORCEM® THERM System.
- The incorporation of the mesh into the profile, makes it quicker to do the corner.

APPLICATION PROCEDURE

- Apply a coat of MORCEM® THERM mortar on the two surfaces that make up the corner, over an area that includes the profile and the mesh.
- Then place the profile on the mortar and press gently.
- With the help of a level, position the profile correctly.
- Cover the top surface of the profile by applying MORCEM® THERM mortar.

RECOMMENDATIONS

- At joints between profiles, leave a separation distance of 2 to 3 mm.
- Once the profile is installed, leave to dry for at least 24 hours.

PACKAGING AND STORAGE

Boxes of 100 units at 250 linear meters.

TECHNICAL DATA

(Data obtained in a laboratory under standard conditions)

Composition	PVC and Fiberglass with anti-alkaline treatment
Mesh weight	0.11 Kg/m
Profile length	2.5 m
Dimensions	

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

MORCEM® THERM PERFIL ÁNGULO PVC CON MALLA

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.