



PUMAFLEX PUMAFLEX

Acrylic rubber for waterproof coating

DESCRIPTION

Product that provides continuous coverage capable of preventing water seepage and the consequent problems resulting from dampness. It is a coating that completely adheres to the surface, with high flexibility, elasticity and mechanical strength, and which withstands excellently the conditions of its application outside and keeps its properties for a very long time due to its excellent durability. It is especially suitable for preventing water seepage in terraces, flat roofs, tiled roofs, party walls, expansion joints, channels, downspouts, etc.... In general, it can be applied on any external surface that may be passable provided that this is not daily or intensive.

TECHNICAL CHARACTERISTICS

Waterproofing coating made up of an aqueous dispersion of acrylic copolymers, loads with high mechanical strength, additives and special pigments.

ADVANTAGES AND USES

- Excellent water tightness and tightness to liquids in general.
- High resistance to traction and to elongation to breakpoint.
- Extraordinary resistance to ageing, to abrasion and puncture.
- Good homogenization of the product and easy application.
- Film resistant to weather conditions and ultraviolet rays.
- Excellent resistance to abrasion.
- Good filling of cracks and resistant to microcracking.
- Greater mechanical strength with the use of fiberglass mesh.
- It does not create a vapour barrier, it allows the substrate to breathe.

SUITABLE SUBSTRATES

NEW SUBSTRATES

- Remove dust, grease and other contaminants.
- Apply the paint according to the instructions for use.
- Concrete, cement, render, brick, stone, fiber cement, etc.... must be set, dry, firm and free of dirt and grease.
- Treat efflorescence or saltpeter with diluted acid solution, rinse and allow to dry.
- The surfaces should be free of moss and microorganisms, dry or slightly damp.
- If there are cracks, holes or chips, repair before applying the product.

OLD SUBSTRATES

- Concrete, cement, render, stone, fiber cement, etc.... must be set, dry, firm and free of dirt and grease.
- Treat efflorescence or saltpeter with diluted acid solution, rinse and allow to dry.
- Remove mold contamination with bleach or other suitable decontaminant, and also remove any loose paint or other building materials.
- On surfaces in poor condition, with lack of cohesion or damp problems, apply a water-repellent sealant beforehand.
- If there are cracks, holes or chips, repair before applying the product.
- Old paint should be brushed to remove loose particles, cleaned and degreased.
- Apply the paint according to the instructions for use.

ACRYLIC RUBBER

PUMAFLEX

APPLICATION PROCEDURE

- Stir until evenly mixed.
- Dilute the first coat by 5% with water.
- Apply the second and subsequent coats undiluted, crosswise to the application of the previous coat.
- For optimum performance and durability of the waterproofing, at least 1.5 l should be used per m² of surface.
- On surfaces that are frequently passed through, fiberglass or polyester cloth reinforcement should be laid on the first undiluted coat. The subsequent cuts of this must be overlapped by about 10 cm, leaving on the top the part that coincides with the fall of the floor slope. The reinforcement must be stretched tight, with no folds and then covered with the subsequent coats of the waterproofing product.
- The application can be carried out with a brush, roller or spray gun after the respective stirring and dilution of the product.
- The tools should be cleaned with water before the paint dries.

RECOMMENDATIONS

- If there are fillers or asphalts in the expansion joints it is recommended to "bridge them" appropriately with polyester elastic reinforcement.
- Where necessary, correct slopes to prevent water from pooling.
- At the joints with vertical surfaces it will be necessary to reinforce with fiberglass or other suitable material applying Pumaflex up to a height of 15 cm.
- Do not apply at temperatures below 5°C.
- Do not apply with relative humidity above 85% or on wet substrates.
- Do not apply under any circumstances if rain is forecast.
- Store in a cool, dry place.

PACKAGING AND STORAGE

Containers of 0.75, 4 and 15L.

Shelf life: 24 months in its sealed original packaging, in a cool, dry place protected from weather conditions and direct sunlight, avoiding exposure to temperatures lower than 5°C or higher than 35°C.

TECHNICAL DATA

(Statistical data obtained under standard conditions)

Binder	Styrenated acrylic
Diluent	Water
Fixed material in weight	61%+/- 0.5
Specific weight	1.25 Kg/l
Viscosity (22°C)	80Pas +/- 10
Theoretical yield	0,8-1,2 L/m ²
Fire Behavior	M1
Drying time	Tack-free 2 hours. Total < 24 hours
Time before repainting	Minimum of 8 hours, according to atmospheric conditions
Resistance to traction	> 10 Kg/cm ²
Elongation to breakpoint	> 300%
Loss of elongation due to accelerated ageing	< 40%
Loss of mass due to thermal ageing	< 10%
Loss of elongation due to thermal ageing	< 35%
Finish	Semi-Matte
Colour	White, Red, Terracotta, Green and Grey

Data consistent with compliance with standard UNE 53413 for "Flexible coatings based on copolymers in aqueous dispersion, without reinforcement, for in situ waterproofing in the construction industry." Applicable on vertical surfaces. Using our MALLAFLEX reinforcements in the way specified in this datasheet, complies with standard 53410 for flexible membranes for in situ application, based on copolymers in aqueous solution, with reinforcement, for waterproofing in the construction industry.

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their

ACRYLIC RUBBER

PUMAFLEX

correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.