

NIVELAND® 5

Self-leveling mortar for layers of up to 5 mm



DESCRIPTION

Self-levelling mortar for indoor floors preparation. Once hardened, it is suitable for all kind of light floorings (tiles, parquet, fitted carpet, etc.).

COMPOSITION

Product based on special cements, selected aggregates and additives.

FEATURES AND APPLICATIONS

- Indoor floor levelling.
- High mechanic resistance.
- Good superficial hardness.
- Easy to apply.
- Excellent fineness.
- Excellent levelling qualities.
- Up to 5 mm thickness.

SUBSTRATES

- Concrete, mortar flooring and similar elements.
- Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products, etc.
- Apply Paviland Primer R to avoid the formation of air bubbles in the cladding and in order to improve its adherence to the substrate according to the instructions given in the technical data sheet of the product.
- If necessary prepare the substrate mechanically so that the surface is free from grout and has the appropriate porosity.
- Before applying NIVELAND 5, any possible hollows and cracks should be adequately repaired using the Paviland or Morcem Rest adequate product, according to the nature of the substrate and the type of reparation required.
- Before applying the paste, make sure that residual moisture is below the recommended proportion (less than 3%).

INSTRUCTIONS FOR USE

- Add water (5.5 to 6 litres per bag) and mix with a low-speed mechanical mixer (500 rpm approx.) until you have an even and fluid paste.
- Let the mixture stand for 2 minutes and remix.
- The manipulation time of the paste is 20 minutes, depending on the weather conditions.
- Pour the mixed product on the base to be set and spread with a levelling trowel.
- The recommended thickness is 2 – 5 mm. applied in one coat.

CAUTIONS AND RECOMMENDATIONS

- Do not apply below 5°C nor above 30°C.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- Do not apply on humid floors or when there is a risk of humidity.

FLOORING LINE

NIVELAND® 5

- Do not add water once it starts to harden.
- Do not apply outdoors.
- On surface areas greater than 20 m², it is advisable to make partition joints (of 6mm minimum), filling them with an elastic material, such as PUMALASTIC MS or PU.
- Movement joints on the original substrate must be respected and perimteral joints made.
- The surface coat should be protected against an extremely fast drying, specially under high temperatures or heavy winds conditions.
- Before placing the final pavement, you should check the residual humidity of the floor and confirm it is adequate for the type of flooring to be installed.

PACKAGING

25 kg plastic-lined paper bags.
6 months in sealed original packaging, sheltered from weather conditions and humidity.

TECHNICAL DATA

(Statistical data obtained under standard conditions)

Aspect	GREY powder
Setting starting time	90 min.
Time to wait before walking on surface	4 - 5 hours
Sanding time	8 - 12 hours
Cladding time tiling or wall-to-wall carpet starting	24 hours later
Cladding time timber, synthetic floor or paint starting	24 hours later
Resistance to compression	>20 N/mm ²
UNE-EN 13813 Classification	CT C20 F6
Resistance to bending	>6 N/mm ²
Approximate yield	1,5 Kg/m ² per mm of thickness

NOTE: Times shown relate to 23°C temperature and 50% relative humidity. Such times are shorter at higher temperatures and longer at lower temperatures.

CE MARK


GRUPO PUMA SL
Avda. AGRUPACIÓN CÓRDOBA, 17 14014 CÓRDOBA 05 Nº:500544-01
EN 13813
NIVELAND 5 Self-levelling mortar for indoor floors preparation, installation of light floorings such as tiles, parquet, fitted carpet, etc. Thickness from 1mm to 5 mm.

ENVIRONMENTAL PRODUCT DECLARATION (EPD)

Fire reaction	Clase A1
Emission of harmful substances	CT
Compressive Strength	C20
Flexural Strength	F6

Cement based mortar prepared with aggregates that are supplied close to the production center, which reduces the greenhouse gas emissions that would otherwise arise from their transport. Manufactured in production centers with an Environmental management certified system following ISO 14001 regulation, offering a firm promise of sustainability and respect for the environment.

Cement based mortar with type III ecological label (the most strict) Environmental Product Declaration verified externally by AENOR.

NOTE

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.