ROUGH



PUMACRIL REVESTIMIENTO RUGOSA PUMACRIL COATING

DESCRIPTION

Rugged coating best for exterior vertical facing of concrete, brick and construction material based on cement.

TECHNICAL CARACTERISTICS

ADVANTAGES AND USES

Great whiteness an opacity.

• Once dry, forms a film impervious to water and pervious to steam.

Product form by aqueous dfispersal of vinyl resin, pigments and special additives.

- Excellent adherence on usual construction supports, be it on cement mortar, plaster, stucco, etc.
- Good resistance to support alkalinity.

SUITABLE SUBSTRATES

NEW SURFACES

- · Eliminate dust, grease and other contaminants
- · Apply a layer of FIJAMOR diluted with 2 or 3 parts of water to equalise support absorption.
- Apply the paint according to instructions for use

ANCIENT SURFACES

- Eliminate mold pollution with bleach or other appropriate decontaminant, as well as loose paint pieces or other construction material.
- Level irregularities with appropriate putty. Leave to dry and sandpaper.
- Apply a layer of FIJAMOR diluted with 2 or 3 parts of water to equalise support absorption.
- The use of hydrofuge sealer is recommended on surfaces in poor conditions, poorly united or with dampness problems.
- Apply the paint according to instructions for use.

APPLICATION PROCEDURE

- Shake until mixture is homogeneous.
- Dilute the first layer between 10-15% of water.
- Apply the second hand and following hands without diluting.
- Apply the first hand with a wool roller and the next with a foam roller to achieve desired decorative effect.
- Cleaning of tools done with water immediately after use.

RECOMMENDATIONS

- Do not apply at temperatures below 5°C.
- Do not apply either with relative humidity greater than 85% or on wet supports.
- Stores in fresh and dry places.

PACKAGING AND STORAGE

4 and 14 L tub.



PAINTS

PUMACRIL REVESTIMIENTO RUGOSA

Shelf life: 1 year in sealed original packaging, sheltered from outside conditions and humidity

TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Colour	WHITE
Viscosity (22°C)	300 dPas
Specific weight	1,75 Kg/L
Approximate Yield	2 at 3 m ² /L
Dry out times	30 min. to tact
Repainting interval	Minimum 3 hours, depending on room temperature

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.

