



PAVILAND® RESINA DC2

PAVILAND® RESIN DC2

Resin for curing concrete

DESCRIPTION

Liquid product best for the concrete curing process in order to promote its maximum performance. Controls hydration water evaporation regulating dry out time and favours slow curing to achieve an increase of final mechanical resistance, achieving more tenacious surfaces and the maximum development of its hardness. Acts on the surface forming a plastic closing capable of eliminating systematically the formation of cracks and of controlling superficial retraction.

ADVANTAGES AND USES

Roads, tracks, industrial floors, etc.

APPLICATION PROCEDURE

- Apply on recently placed concrete, taking into account that the entire surface must be completely covered.
- Must be applied spraying at a distance of 30-40 cm from the surface, making sure to leave a uniform film, without excessive product accumulation and avoiding overly thick layers.
- The tools used must be cleaned with xylene or universal solvent.

RECOMMENDATIONS

- Do not apply below 5°C nor above 35°C.
- Substrates must be clean, dry, free of grease, fissurews or materials disintegrates.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- Adequate ventilation must be available in closed areas during the time of application and drying of the product.
- Work Risk Prevention Laws shall be observed at all times.
- Toxic when inhaled, ingested or when in contact with skin and/or eyes.
- Do not eat, drink or smoke during application.
- Maintain away from sources of heat. Sheltered and well sealed.
- Apply with spray gun only in areas with good ventilation. Use respiratory safety equipment when necessary.

PACKAGING AND STORAGE

25 l. buckets.

Store up to two years in sealed original packaging, sheltered from weather conditions and humidity. Do not expose to temperatures below 5°C nor above 35°C.

TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Binder	Hydrocarbon resin
Solvent	Organic solvent
Density (20°C)	0,88 ± 0,02 g/cm ³
Solubility	In most aromatic hydrocarbons
Solid content	18,0 ± 0,5%
Category according to R.D. 227/2006	A/h (BD)

LEGAL DISCLAIMER

COVs	Lím. 2007-10:750; max: 738 g/L
Approximate yield	10-12 m ² /L

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.