



MORCEM® TEXTURE

One-coat mortar for stamped finish



DESCRIPTION

One-coat mortar.
Specially designed for texturing of interior and exterior coatings.
For hand or pump application directly on the brick.
Rainwater proof and permeable to water vapour.
Wide range of decoration possibilities by combination of colours and textures.

TECHNICAL CHARACTERISTICS

Product based on high resistance cement, selected aggregates, special additives, pigments and synthetic resins.

ADVANTAGES AND USES

- To be applied directly on the brickwork. No need for a previous plastering.
- To be applied indoors and outdoors.
- Waterproof cladding.
- Permeable to water vapour, allowing the substrate to breathe.
- No cracking.
- Wearing resistant. Fading resistant.
- Wide range of decorative finishes by application of molds or rollers.

SUITABLE SUBSTRATES

- Conventional cement and brickwork based substrates.
- Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products, etc.
- In case of hot or windy weather conditions or when applying over absorbent substrates, it is advisable to wet the substrate and wait until the thin layer of water disappears.
- In particular points (union between different materials, top slabs, pillars, roller blind boxes, angles in the door and window frames, etc.), prepare the mortar with glass fiber mesh to avoid fissures.
- With low-porosity substrates, apply a priming coat (IMPLAFIX) or improve roughness by mechanical means.
- Do not apply on clay or on paint.

APPLICATION PROCEDURE

The stamped one coat mortar requires to follow a series of steps during application which are not very different from conventional rendering jobs.

The steps to be taken are as follows:

- Reinforce the substrate with a mesh on stressed areas and prepare partition joins as in a conventional one-coat system.
- Mix preferably by mechanic means until a homogenous paste is obtained.
- Spread a layer of 10mm max on the substrate. Thicker coatings can be achieved depending on desired finish texture.
- Wait for 15-20 minutes (depending on weather conditions this may vary) before texturing MORCEM TEXTURE. When the product does not adhere to the naked fingertip it is a good indication that the product

DECORATIVE PLASTERS

MORCEM® TEXTURE

RECOMMENDATIONS

- is ready to be textured.
- Spray a small quantity of demolding liquid DESMOLDEANTE MORCEM TEXTURE on the render and on the mold/roller. To ensure the substance does not stick, apply again the separating demolding agent to the roller approximately every 2m.
- Run the roller on the render to create a pattern. Adequate pressure must be exerted. Hard enough so the stamping is clear but soft enough not to produce pressure waves on the render. Small stamping defects should be fixed immediately during the stamping process. Either when applying the substance, or when applying it to the roller, if the edges are stained with paste as in continuous grooves, this effect is not necessarily aesthetically pleasing and should be corrected at the time.
- Option: 24 hours after application MORCEM TEXTURE can be pigmented by moistening the texture and spreading a dilution of one or many pigments on the stamped render.
- Option: To increase the resistance of the finish, spray RESINA MORCEM TEXTURE on the exiting MORCEM TEXTURE, otherwise use a roller with the lowest yield possible (white foam roller or varnish roller). Apply an even coating so avoiding the generation of straight lines of excess product which may yield a poor finish.

- Do not apply below 5°C nor above 30°C.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- It is not advisable to apply on horizontal or sloped surfaces.
- Take care not to contaminate/stain other surrounding elements when spraying RESINA MORCEM TEXTURE

PACKAGING AND STORAGE

25 kg plastic-lined paper bags.
Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.

TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Aspect	WHITE or COLOURED powder
Molding time	15-20 min. depending on weather conditions
UNE-EN 998-1 Classification	OC CSIII W2
Approximate yield	18 Kg/m ² per cm of thickness
Float time	1-2 hours

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.