# Rev. 25\_01 · This revision cancels all previous ones. Please, obtain the latest version from our web site · www.grupopuma.com · (+34) 957 76 40 40

### **DECORATIVE PLASTERS**



# **MORCEM®** ESTUCO EXTRA FINO

Colored rendering and finishing mortar







### DESCRIPTION

Rendering and decoration lime mortar for both interior and exterior walls.

# TECHNICAL CARACTERISTICS

ADVANTAGES AND USES

### · Excellent adhesion.

- Suitable for interior and exterior use.
- Avoids any paint. Decorative finish façade.
- Environmentally friendly, product included in the "Green Line".

### **SUITABLE SUBSTRATES**

## APPLICATION PROCEDURE

It should always be applied over a smooth base of MORCEM ESTUCO FINO.

- Add 2.7 litres of water per 3 kg container and mix manually or mechanically until a homogeneous, workable consistency free of lumps is achieved.
- Apply MORCEM ESTUCO EXTRAFINO on a MORCEM ESTUCO FINO base.
- Spread the mixed product.
- Spread the kneaded product with a stainless-steel trowel with less than 1 mm thickness.

Product based on aerial lime, aggregates with balanced granulometry, and other additives.

• Smooth the surface with a stainless-steel trowel until getting a polished texture.

### **RECOMMENDATIONS**

- Do not apply directly onto the masonry (brick, concrete block, etc.) as this material is strictly decorative and should always be applied over MORCEM ESTUCO FINO.
- Do not apply the product under 5°C nor above 30°C temperature.
- Do not apply under the risk of frost, rain, heavy wind, or direct sun light.
- It is not advisable to apply it on horizontal or leaning surfaces.

# PACKAGING AND STORAGE

3 kg polyethylene plastic-coated paper bags.

Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.



### **DECORATIVE PLASTERS**

# **MORCEM**® ESTUCO EXTRA FINO

### **TECHNICAL DATA**

(Statistic results obtained under standard conditions)

Aspect	White
Application thickness	1 mm
Powder density	0.6 g/cm <sup>3</sup>
Mass density	1.4 g/cm <sup>3</sup>
UNE - EN 998-1 classification	CR W0
Performance	0.3 Kg/m <sup>2</sup>

# ENVIRONMENTAL PRODUCT DECLARATION (EPD)

This mortar has been elaborated with arid located close to our production centres, which has, reduce the emission of greenhouse effect gases thanks to transport and ISO 14001 certified production centres with environmental management, with a firm commitment to sustainability and respect for the environment.

Type III eco-friendly labelled mortar (The strictest one) verified. Environmental Product Declaration by AENOR

### **LEGAL DISCLAIMER**

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.

