

TEXTUREFIX PLUS



DESCRIPTION

TEXTUREFIX PLUS is a priming product for use in construction as a bonding coat between new and old mortar. It has a good penetration and cohesion capacity due to the size of the particles. It is also capable of improving adhesive conditions on vertical substrates as a prior step to applying facings. Recommended as a bonding agent for paintwork, especially on plaster facings, perlite and old substrates. It also acts as a primer for regulating the absorbency of substrates such as cellular concrete or silico-calcareous brick, suitably treating substrates with high humidity or irregular absorption levels in order to keep the plasterwork uniformly hydrated after plastering.

TECHNICAL CHARACTERISTICS

Acrylic copolymer based emulsion with very small particles, in aqueous emulsion.

ADVANTAGES AND USES

- TEXTUREFIX PLUS is particularly suitable for using as a primer before applying our coloured mortars PAVILAND PLUS, levelling pastes NIVELAND 3-5 Y 10R (horizontal substrates), MORCEM TEXTURE (vertical substrates) and generally any type of coloured, repair, or polished mortar, etc.
- As a primer on anhydrite substrates, prior to applying cement-based adhesive.
- Increases resistance to flexo-traction fractures as well as the system's cohesion and permeability.
- High penetration of the substrate.
- Good adhesion, favouring the posterior application of the facing.
- Efficient homogenisation of the substrate's absorbance.
- Good cohesive capacity on inconsistent substrates.
- Outdoor use should be avoided if there is a risk of rain or ice.

SUITABLE SUBSTRATES

HORIZONTAL SUBSTRATES

- Substrates must be clean and free from grease, oil, oxides, remains of paint and loose or badly bonded parts.
- Spread the product directly with a sprayer, ensuring a uniform covering, without excessive accumulation of product and avoiding thick layers.

VERTICAL SUBSTRATES

- Substrates must be clean, dry and well bonded.
- Apply an undiluted coat of product with a brush, roller or spray gun.

APPLICATION PROCEDURE

- Shake until the product is even.
- Dilute the product up to 50% according to the substrate's absorbency.
- Apply with a brush, roller or spray gun.
- Do not apply quantities that form a film or thick layers.
- Drying time to the touch: 60 minutes.
- Wait between 24 and 48 hours before applying mortar or cement glue.

ADDITIVES AND PRIMERS

TEXTUREFIX PLUS

RECOMMENDATIONS

- Clean work tools with water immediately after use.
- On anhydrite, plaster and non-absorbent or similar substrates, use undiluted product as a treatment prior to applying mortar, levelling paste or cement glue.
- On substrates with a high absorbency level, dilute the product up to 50% prior to plastering.
- As a paint primer dilute the product up to 1-2 parts with water.

- Do not apply the product at ambient temperatures lower than 5°C or higher than 35°C.
- Do not apply if there is a risk of ice or rain, nor with a relative humidity higher than 85%. Do not apply in direct sunlight.
- It is advisable to wear gloves while handling the product.
- TEXTUREFIX PLUS is not toxic, hazardous or flammable in normal handling conditions. It is not necessary to use special safety measures and strictly adheres to the provisions set forth in the Occupational Risk Prevention Law.

PACKAGING AND STORAGE

Packages of 5 and 25 L.

Shelf life: In sealed original packaging, sheltered from weather conditions and humidity and away from intense cold and heat: 2 years.

TECHNICAL DATA

(Statistical data obtained under standard conditions)

Solvent	Water
Specific weight	1.03 kg/L
Performance	From 6 to 8 m ² /L according to substrate
Dried to the touch	60 mins.
Repainting time	8 hours minimum

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.