

MALLA DRYPOOL DRYPOOL MESH



DESCRIPTION

Morcem®Dry Mesh consists of double weave threads, essential for the reinforcing.

Recommended in the application of swimming pool waterproofing systems as DryPool. Gives the system great resistance and stability, and prevents the appearance of cracks caused by temperature differences or movements.

TECHNICAL CHARACTERISTICS

Fiberglass threads covered by an special resin which protects them from alkaline attack of mortars.

ADVANTAGES AND USES

- Easy to apply.
- High alkalis resistance.
- Crack resistant.
- Great mesh stability.
- Test methods according to DIN 53 854 part2.
- Test methods according to ISO 13 934-1.

APPLICATION PROCEDURE

Apply like a sandwich.

- Apply a first layer of Traditerm mortar onto the substrate and place the mesh so that it is slightly embedded.
- Apply a second layer of MorcemDry mortar to completely cover the mesh.

RECOMMENDATIONS

Handling this product does not require special care, although, it can cause irritation to very sensitive skin. If this should happen, wash with sufficient cold water and soap.

PACKAGING AND STORAGE

100 cm x 50 m rolls.
Store vertically in a dry place protected from exposure to the sun.

TECHNICAL DATA

Composition	100% fibreglass
Screen size	2.4 x 2.4 mm
Mesh weigh	60 g/m ²
Tensile strength - Weave	Aprox 650 N/5 cm
Tensile strength - Warp	850 N/5 cm
Extension to the breakage - Weave	3.75% ± 0.27
Breakage resistance - Warp	3.17% ± 0.26
Chemical resistance	Good resistance to alkalis

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their

CONCRETE REPAIR

MALLA DRYPOOL

correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.