

# MORCEM® CAL BASE

Natural hydraulic-lime mortar for rendering. Natural composition, highly breathable.







#### DESCRIPTION

Natural hydraulic lime lining mortar. Natural composition, highly breathable.

## TECHNICAL CARACTERISTICS

ADVANTAGES AND USES

## Product based on lime, selected aggregates and other additives.

- Highly permeable interior and exterior coating
- Highly compatible with traditional systems and so suitable for renovation use.
- Application on newly built interiors and exteriors for enhanced habitability conditions compared with cement-based mortars.
- Permeable to water vapour, allowing the substrate to breathe.
- Excellent adherence
- · Great plasticity.
- Smooth, sponge floated or rougth finish.
- · Contains no cement.
- · Apply by hand or with a pump.
- · Plaster and stucco works.
- · Filling of joints in masonry and masonry.

#### **SUITABLE SUBSTRATES**

- · Conventional surfaces based on hydraulic binders, brickwork and masonry.
- Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products, etc.
- Wet the substrate and wait for the water film to disappear
- With low-porosity substrates, apply a priming coat (IMPLAFIX) or improve roughness by mechanical means.
- Do not apply on clay or on paint.
- Refurbish any areas with lack of cohesion or weak areas in the support. Remove loose parts of masonry
  and re-clad with MORCEMCAL MURO. To improve the adherence of the rendering, use a sunken finish
  for joints between masonry parts. Avoid using mortars with cement to prevent formation of salts or salt
  deposits on the masonry.



### LIME LINE

### MORCEM® CAL BASE

#### **APPLICATION PROCEDURE**

To ensure good compatibility between the surface and the coatings, take the following steps:

- · Wet the substrate copiously until saturated and wait for the surface shine to disappear before applying a uniform layer of Morcemcal Base with an approximate thickness of 0.5 cm. to prevent the appearance of cracks in subsequent layers. Cure the applied material 24 hours after application. The surface should be rough even though it is regulated to remove any excess mortar that may have accumulated in some
- · On the following day, moisten before applying MORCEMCAL BASE, mixed by mechanical means, with a thickness from 0.8-1.5 cm using a trowel or projection machine. Although mortar admits a greater thickness, better results are obtained by superposing mortar layers until reaching the desired thickness, as this favors carbonation. Apply the product preferably using a wood float and then proceed to straightedging and subsequent troweling.
- If it is necessary to apply a greater thickness to level for any differences, wait at least 48 hours before applying between layers, leaving the surface rough to optimise the adherence between each layer.
- Before finishing coats with MORCEMCAL ACABADO, wait 24-48 hours per centimetre of mortar base coat. Always wet substrates before a multilayer application.

#### **RECOMMENDATIONS**

- To achieve waterproof coatings it is necessary to finish the mortar with MORCEMCAL ACABADO.
- Do not apply at temperatures below 5°C nor above 30°C.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- For a thickness of over 1,5 cm, it is advisable to apply the product in two coats.
- It is advisable to spray water gently on the product the day after it is applied.
- The mortar must not be stronger than the support.
- Remove any dust, dirt or salt blooms from the wall.
- · Moisten the wall generously.

and humidity.

- · Superposing layers on the wet mortar ensures good adherence and aids carbonation.
- Adjust the mixing water, avoiding excesses, until the desired consistency is reached by mixing (3-5 min.) .Do not add water to the already mixed mortar.
- The natural origin of the raw materials used in the Morcem Cal mortars, may cause slight changes in color between different production batches.

25 kg plastic paper bags. Shelf life: 1 year in sealed original packaging, sheltered from weather conditions

## **PACKAGING AND**

(Statistical data obtained under standard conditions)

### **STORAGE**

Aspect Range of colours Water vapour permeability µ ≤6 UNE EN 998-1 Classification CR CSII W1 Approximate yield 16 kg/m2 per cm of thickness

#### **TECHNICAL DATA**

**ENVIRONMENTAL PRODUCT DECLARATION (EPD)**  Argamassa elaborada com agregados próximos dos centros de produção reduzindo as emissões dos gases de efeito de estufa associados ao seu transporte e elaboradas nos centros de produção com sistemas de Gestão Ambiental certificados de acordo com a norma ISO 14001, pelo que confere um firme compromisso com a sustentabilidade e o respeito pelo meio ambiente.

Argamassa com etiqueta ecológica tipo III (a mais exigente) Declaração Ambiental de Produto verificada externamente pela AENOR.



### LIME LINE

## MORCEM® CAL BASE

#### **LEGAL DISCLAIMER**

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.

