



PAVILAND® TRAFFIC 15 R AUTONIVELANTE

Rapid Self-levelling coating for indoors applications in premises of intense pedestrian traffic and light parking traffic



DESCRIPTION

Self-levelling coating, fast drying, which hardened once creates a coating of high flatness, high mechanical strength and excellent adhesion on the support application. Suitable for thicknesses between 5 and 15 mm. This self-levelling coating boasts ease of laying and excellent adhesion to cementitious mortars and concrete. It has great levelling capacity and is ideal for use in cold weather. Renovation of parking pavements.

TECHNICAL CHARACTERISTICS

Product based on selected aggregates, cement, resins and additives.

ADVANTAGES AND USES

- Facility of laying
- Excellent adherence on cement mortars and concrete
- Large capacity leveling
- Ideal for use in cold season, where normal drying self-leveling coatings require a longer start-up time.
- Fast commissioning.
- System for repairing or patching of floor and damaged pavement in indoors
- Leveling of irregular pavements in indoors
- Smoothing of floors in interior premises of pedestrian traffic, prior the placement of the final pavement: carpet, linoleum, PVC, etc.
- Fine coat levelling of indoor floors in car parks with moderate traffic before finishing with paints from the PAVILAND PINTURAS or PAVILAND RESINAS range.

SUITABLE SUBSTRATES

- Concrete, slabs surfaces, of adequate strength, and similar. For other supports please contact our technical department.
- Support should be resistant, stable, healthy and clean, free of dust, remains of gratty, organic products, etc.
- If necessary, the dough should be prepared by mechanical means, to make this a surface without grout and proper porosity.
- Before the application of PAVILAND TRAFFIC 15 R AUTONIVELANTE, we must repair adequately the hollows and / or fissures that they could find in the support using the range Paviland or Morcem Rest according to the nature of the support and the type of repair that we have to do.
- Applies the priming Paviland Primer R to avoid the formation of air bubbles in the coating and to improve its adherence on the support.
- Before applying the dough, make sure that residual moisture is below recommended (less than 3%).

APPLICATION PROCEDURE

- Define and mark the maximum height of the sill.
- The pouring area must be established avoiding areas with different setting times, for which the means

FLOORING

PAVILAND® TRAFFIC 15 R AUTONIVELANTE

RECOMMENDATIONS

- available for carrying out the work, the environmental conditions and the open time of the mortar must be considered. Confining pouring areas beforehand can also be used to make partition joints, avoiding them being made later by cutting.
- Knead with water (4, 125-4, 625 l per 25 Kg sack) mechanically, with a mechanical mixer, low-speed (approx. 500 rpm) until you obtain an homogeneous and smooth dough. The exact dosage of water is very important to avoid segregation of product, high retraction and reduction of resistances.
- Let the dough about 2 minutes.
- For the accomplishment of big surfaces the pumping of the mixture is advisable with spiral bombs of double kneaded and that stimulate 20 to 40 L/minutes. This operation allows the optimization of the times of implementation at work.
- Extend manually with a metallic trowel once the primer has hardened. Then pass a roll of nylon prongs.
- Respect the structural joints and complete perimeter and partition joints.
- Paviland Traffic 15 R AUTONIVELANTE should be protected because it is not a material ready to be seen. Before being covered by the range of painting PAVILAND PINTURAS, resin pavement or pavement stuck, you will maybe need to prepare the surface to remove the grout surface. The maximum moisture requirements of the final coating must also be taken into account.

- Do not apply below 5 ° C or above 30 ° C.
- Do not apply with risk of frost, strong winds or direct sunlight.
- Do not apply in interiors.
- Do not apply to floors with humidity or with risk of having it.
- Keep in mind the working time of the product for the planning of the work.
- Wear gloves and safety glasses for use. Keep out of the reach of children.
- Do not add sand, cement or any type of product that modifies the original formulation.
- Once the product kneaded and its rest time has elapsed, do not add any extra water.
- For paves with superior surfaces to 20 m² or more than 10 linear M, the accomplishment of partitions joints is recommended, delimiting slabs, with joints of approximately 6 mm that will be refilled by PUMALASTIC MS or PU.
- Movement joints will have to be respected of the original support and complete perimeter joints.
- The surface layer has to be protected from too fast drying, especially in conditions of high temperature or strong wind.
- Before laying the final pavement the residual dampness of the pave, must be verified and arranged according to the type of pavement to lay.

Sacks of 25 kg of plasticized paper.

Storage up to 1 year in original package closed, sheltered from the weather and humidity.

(Statistical results obtained under standard conditions).

Appearance	Grey powder
Open time	20 minutes
Expansion - retraction	< - 0.5 mm/m
Opening time pedestrian traffic (*)	12 hours
Opening time traffic (*)	7 days
Time for sanding (*)	24 hours
Time for coating (*)	3 days
Resistance to compression	> 10 n/mm ² (24 hours) > 20N/mm ² (7 d) > 30 n/mm ² (28 d)
Approximate performance	17 - 19 kg/m ² and cm of thickness
Classification according to UNE EN 13813	CT C30 F5
Thickness Application	5 to 15 mm adhered slabs

(*): The times refer to a temperature of 23°C and 55 % of relative dampness. These are shorter with higher temperatures and longer with lower temperatures.

LEGAL DISCLAIMER

FLOORING

PAVILAND® TRAFFIC 15 R AUTONIVELANTE

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.