

PAVILAND® TOP EPW

Coloured epoxy paint, water-based, for the protection of concrete surfaces and cementitious base coat.



DESCRIPTION

Water-based epoxy resin coating, consisting of two components that harden through a chemical reaction and are tolerant to substrates containing some residual moisture. This flooring product exhibits extraordinary adhesion to the substrate, even on wet surfaces. It is also permeable to water vapour and various aggressive agents. Among its characteristics are easy application and being odourless, making it ideal for use in indoor, poorly ventilated garages.

TECHNICAL CHARACTERISTICS

Two-component water-based epoxy sealing render.

ADVANTAGES AND USES

- The product exhibits exceptional adhesion to the substrate, even on wet surfaces. Easy to apply.
- Odourless.
- Surface hardener of the substrate.
- Permeable to water vapour and resistant against a great number of aggressive agents.
- Tools must be cleaned with water.
- Dust-repelling effect.
- Garages.
- Warehouses.
- Chemical industry.
- Hygienic cleaning: non-porous surfaces which are easy to clean.

SUITABLE SUBSTRATES

- Concrete or self-leveling cementitious material with a suitable resistance (25N/mm² minimum compressive strength and 1,5 N/mm² resistance to traction) open porous and light roughness. Please consult our technical department for a different type of substrate.
- Substrates must be resistant enough, stable, sound and clean. Free of dust, release agents, organic products, etc.
- Before applying any product make sure all holes and / or cracks are previously repaired on the substrate by using products from our PAVILAND or MORCEMREST range.
- It is also advisable to carry out a milling or sanding process of the substrate with the main objective of opening the porous and removing any possible adhered materials such as greases, paints, etc.
- The maximum allowable residual moisture content of the substrate must be less than 6%.

APPLICATION PROCEDURE

- Homogenize components A and B separately.
- Pour component B on top of component A and mix them with a suitable mixer at low speed, until getting a homogeneous product.
- Apply a first coat using a brush, short-haired roller, or airless method. This coat can be thinned down (10-15%) with water to be used as a primer.
- The second coat, undiluted, is applied within the time-frames indicated in the schedule available at the end of this technical data sheet. Please note that these time frames are approximate and depend on environmental features.
- Finish must be smooth and uniform. Uneven application or different thicknesses of the product might cause variations in the floor's tone.
- Cover the flooring for at least 48 hours following its application.

RECOMMENDATIONS

- Do not apply the product under 10°C due to the potential resin crystallization. Do not apply it above 30°C.
- Do not apply under the risk of frost, rain, heavy wind or direct sun light.
- The product changes tone or may experience discolouration when used outdoors or exposed to UV radiation; hence, it is recommended for indoor use only.
- Use gloves and protective goggles when manipulating the product. In case of direct skin or clothes contact, clean the area with abundant water.
- Keep away from children.
- The substrate should not be waterlogged. The maximum moisture content should be 6%.
- Low temperatures or intervals exceeding 48 hours between coats can cause coverage issues between coats.
- Excessive thickness in its application may cause differences in shine and/or cloudiness in the final appearance of the floor.
- Any equipment and tools will be cleaned with water immediately after being used. Once the product gets hard, it will only be removed by mechanical means.
- Do not eat or smoke when manipulating the product.
- Empty containers should be removed or thrown according to the current legislation.
- As a consequence of the change in raw materials, the shades of the coloured mortars may vary slightly by batch.

PACKAGING AND STORAGE

Containers of 5 kg (4.05 + 0.95) and 20 kg (16,20 + 3,80).

The product can be stored for up to one year in its original sealed containers, in a dry and well-ventilated area, at temperatures between 10°C and 30°C, and out of direct sunlight and protected from the elements.

COLOUR RANGE

RAL: 3013, 3020, 6001, 6011, 7001 and 7037. Other colours on request.

TECHNICAL DATA

(Statistical results obtained under standard conditions).

Appearance	Liquid
Approximate density of the mixture	1.2 kg/dm ³
Weight ratio of the mixture (A: B)	81 : 19
Adhesion to concrete	> 2 N/mm ²
Approximate yield	150–200 g/m ² and layer

Time of application

	Temperature	Time
Mixture duration	+ 30 °C	~ 20 minutes
	+ 20 °C	~ 35 minutes
	+ 10 °C	~ 60 minutes
Initial curing	24 - 48 hours/ temperature	
Total curing	7 days	
Time for pedestrian transit	24 - 48 hours/ temperature	
Time for light traffic	5 days	
Time for heavy traffic	7 days	
Time to repainting	12-16 hours, but always within 48 hours	
Drying time to touch	8 - 12 hours / temperature	

Timings are given according to temperatures of 23°C and 55% relative humidity. Periods of time will be shorter at higher temperatures and longer at lower temperatures.

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the

supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.