



MORCEM® RENOVEX F



DESCRIPTION

Mineral mortar for the regularization, levelling and smoothing of surfaces with a thin finish, suitable for absorbent and non-absorbent supports, for white interior and exterior areas.

TECHNICAL CHARACTERISTICS

Special cement base product, selected aggregates and additives, reinforced with fibres.

ADVANTAGES AND USES

- Specially designed for the regularisation and restoration of façades avoiding the re- making of the existent render.
- Regulations for and renovation of ceramic surfaces or glass mosaics.
- Regulations for and renovation of surfaces with top coats or existing mortar.
- Regulations for painted surfaces – adhesive paints.
- Regulations for smoothing of interior ceramic linings.
- Great adherence to concrete, paints, ceramic, vitreous mosaic, one-coat mortars, plasterboard and regular plaster (With previous application of a primer like Texture Fix Plus).
- Waterproof to rain water.
- Permeable to water vapour.
- Retraction compensated to decrease cracks risk.
- Interior and exterior application.
- Weather-resistant.
- Great workability.
- R1 according to EN 1504:-2

SUITABLE SUBSTRATES

- Revise the substrate and remove the parts that are not well-adhered. The substrate should be healthy, clean, cohesive, and free from greases, oils dust and bad-adhered parts.
- Absorbent substrates should be previously humidify until saturated avoiding water logging. Apply the product once the surface is completely matt.
- In gaps angles, place Traditem 20x40cm mesh and fix them with Morcem Renovex F mortar. The grids of the mesh, even if they are covered by the mortar, should be marked.

APPLICATION PROCEDURE

Mortar preparation

Add 6-7 litres/water per each 25 kg bag; mix it with a mechanic mixer at low speed. You should get a homogeneous paste free from lumps. Do not prepare excessive material if it is not going to be used during the following 30 minutes (at+ 20°C).

Application of the mortar

Apply Morcem Renovex F with a trowel, pressing, in order to assure the adherence and compact the material firmly.

On absorbent surfaces, spread a first layer of the product, adding extra pressure in order to remove any possible air inside the porous.

Once the mortar has been spread, it is advisable to comb it, with the help of a dented trowel of 6 mm in order

PRE-MIX PLASTERS AND MORTARS

MORCEM® RENOVEX F

to get a homogeneous spreading of the product along the surface.

In this first layer of Morcem Renovex R, soak the Traditerm mesh and smoothen it. Between adjacent meshes make overlaps of 10 cm. The maximum thickness of this first layer with the mesh should be below 3 mm.

Once the reinforced layer is dry, with the help of a trowel, we will proceed to add a second layer of Morcem Renovex F.

The finish of this second layer can be done by a steel trowel, or a sponge.

The application of Morcem Renovex F (2 layer + Traditerm mesh reinforcement) should have a final thickness between 3 and 6 mm.

For interior applications, the same process should be carried out, however the Traditerm mesh is not necessary

Curing

During especially warm days, we suggest pulverizing water on top of the Traditerm Renovex F surface after 4 hours of its application and in the posterior days once the mortar has already hardened, in order to avoid the apparition of cracks.

Finish

For the application of any of the possible finishes, it is necessary to wait a minimum of 48 hours after the application of the last coat of Morcem Renovex F.

The admissible finishes would be Gama Morcemcrl, Gama Pumacril, Morcem Estuco Fino and Pumaplast (indoors).

RECOMMENDATIONS

- Do not add to the mix more than the suggested water nor re-mix it.
- Do not apply it with temperatures under 5°C or above 35°C.
- Do not add cement, sand or any other substances that might affect the properties of the material.
- The tools should be cleaned with water immediately after their use.
- Consult our Technical Department for any application that might not be specified in this Data Sheet.
- For further information regarding the safety in the handling, transport, storage and use of the product, consult the updated version of the Safety sheet of the product.

PACKAGING AND STORAGE

25 kg bags.

1 year storage in its original packaging, away from extreme weather conditions and humidity.

PRE-MIX PLASTERS AND MORTARS

MORCEM® RENOVEX F

TECHNICAL DATA

(Statistic results were obtained under standard conditions)

Aspect	white powder
Paste density	Aprox. 1.7±0,1gr/cm ³
Granulometry	D max 0.5 mm
Thickness of the layer	3mm max. per layer
Maximum thickness of application:	6 mm
Life time of the paste	30 min
Hardening time (at 20°C)	
- Beginning	5h
- Finish	7h
Waiting time before painting	48 h
Performance	1.3 Kg/m ² mm
Classification according to EN 1504-3:2006	R1
Type	PCC

REQUIREMENTS GP PLASTER MORTAR GP 998-1	PRODUCT DATA
Capillary water absorption	W2
Water vapour permeability	μ<10
Adhesion	≥ 2 N/mm ²
Thermal conductivity	0.48 W/m.K

REQUIREMENTS PRODUCTS FOR SURFACE PROTECTION 1504-2	PRODUCT DATA
Water vapour permeability	class 1
Capillary water absorption	W ≤ 0.3 kg/m ² h ^{0.5}
Part thermal compatibility	≥ 2.0 N/mm ²
Tensile adhesive force	≥ 2.0 N/mm ²

PRE-MIX PLASTERS AND MORTARS

MORCEM® RENOVEX F

CE MARK

	
GRUPO PUMA SL Avda. Agrupación Córdoba, Núm. 17 14014 Córdoba 16	
MORCEM RENOVEX F Nº 803525 EN 1504-2	
Mineral mortar for the regularization, levelling and smoothing of surfaces with a thin finish, suitable for absorbent and non-absorbent supports, for interior and exterior areas. In white colour.	
Water vapour permeability	Class 1
Capillary water absorption	$\leq 0.3 \text{ kg/m}^2\text{h}^{0.5}$
Thermal compatibility part 1 y 4	Correct
Adhesive strength by tensile test	$\geq 2\text{N/mm}^2$

	
GRUPO PUMA SL Avda. Agrupación Córdoba, Núm. 17 14014 Córdoba 18	
MORCEM RENOVEX F Nº 803525 EN 998-1	
Mineral mortar for the regularization, levelling and smoothing of surfaces with a thin finish, suitable for absorbent and non-absorbent supports, for interior and exterior areas. In white colour.	
Water vapour permeability	W2
Capillary water absorption	$\mu < 10$
Adhesion	$\geq 2 \text{ N/mm}^2$
Thermal conductivity	0.48 W/mK

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

PRE-MIX PLASTERS AND MORTARS

MORCEM® RENOVEX F

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.