



TRADITERM® PERFIL ÁNGULO ARCO

DESCRIPTION

Used in the Traditerm System. Reinforcing profile for the formation and reinforcement of arcs and circular gaps. Its fast and easy to apply. The profile can be easily folded and adapted to the curvature of the edge that needs to be reinforced. The minimum curvature diameter is 1m.

TECHNICAL CHARACTERISTICS

PVC profile with fibreglass mesh with anti-alkali treatment.

ADVANTAGES AND USES

- Perimeter reinforcing in arcs and circular gaps.
- Fast and easy to apply.
- The profile can be easily folded and adapted to the curvature of the edge that needs to be reinforced. The minimum curvature diameter is 1m.

APPLICATION PROCEDURE

Apply Traditerm mortar layer on both the surfaces that define the edge, from the profile to the mesh. Place the TRADITERM® PERFIL ÁNGULO ARCO on top of the mortar, following the curvature made by the corner that requires reinforcement and press gently. Cover the upper face of the profile and the mesh with Traditerm mortar.

RECOMMENDATIONS

Once the profile has been placed, let it dry for 24 hours minimum.

PACKAGING AND STORAGE

50 units box->125 lineal meters.
profile should be stocked up in horizontal position.

TECHNICAL DATA

Composition	PVC and fibreglass with anti-alkali treatment
Profile length	2.5 m

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the

conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.