



MORCEMSEC® ENLUCIDO FINO CON CAL

Dry mortar for up to 10 mm plaster thickness with a smooth and thin finish.



DESCRIPTION

Cladding mortar based on aerial lime. Suitable for being plastered in a thin layer on top of rough-coating cement mortars. Impervious to rainwater and highly permeable to water vapour.

TECHNICAL CHARACTERISTICS

Product based on aerial lime and hydraulic binders, selected aggregates and additives.

ADVANTAGES AND USES

- Interior and exterior application.
- Suitable for both, new construction and rehabilitation.
- High permeability to water vapour and impermeability against rain.
- Improvement of habitability.
- Manual or mechanical application.
- Smooth and trowelled finish.
- Great adherence.
- Excellent workability, its high plasticity facilitates the execution of the work at any time.
- Between 5 to 10 mm application thickness.

SUITABLE SUBSTRATES

- Mortar plaster, or other substrates of a similar mineral nature with a certain degree of porosity.
- The substrate must be resistant, stable, healthy and clean, free of dust, remnants of release agents, organic products, etc.
- The compatibility of the resistance of the substrate with that of the mortar to be used must be taken into account.
- In case of heat, wind or on highly absorbent substrates, it is convenient to moisten the substrate and wait for the superficial shine of the water to disappear.
- Do not apply the product on top of gypsum plasters or paint.

APPLICATION PROCEDURE

MECHANICAL APPLICATION

- Establish, according to the chosen machine (section and hose length), external weather conditions and optimal water / mortar ratio.
- It is very important to maintain the variables constant as they may affect the features of the applied mortar (wall distance, application angle and water proportions).

PRE-MIX PLASTERS AND MORTARS

MORCEMSEC® ENLUCIDO FINO CON CAL

RECOMMENDATIONS

MANUAL APPLICATION

- Add water and mix it manually or mechanically until getting a homogeneous and workable consistence. Spread the mixed product with the help of a trowel on the substrate.
- It is advisable to apply a well compacted first hand of 2 or 3 mm to seal the substrate, then spread the rest of the material.

Let it rest for the corresponding amount of time and then trowel or smooth the area according to the finish wanted.

- Do not apply below 5°C nor above 30°C
- Do not apply the product under extreme weather conditions.
- Do not apply it under the risk of frost, rain, heavy winds or direct sun light.
- Carry out an adequate treatment of singular points, such as slabs, pillars, window angles, etc., assembling the product with fibreglass mesh to avoid cracking, insert it in the central part of the thickness of the cladding.
- In areas of low absorption it is recommended to use a suitable primer like IMPLAFIX, (see technical data sheet).
- Carry out a good joint design, foreseeing expansion joints, structural ones, as well as those others that could be necessary.
- Minimum application thickness of 5 mm; for a thickness greater to 1 cm it is recommended to apply the product in two layers. The minimum final thickness of a coating mortar must be at least 10 mm to ensure impermeability to rainwater depending on the components of the system on which it is applied.
- In extreme weather conditions (high wind or high temperatures) it is necessary to gently spray the product with water the day after its application.

PACKAGING AND STORAGE

25 kg plastic-lined paper bags.

Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.

TECHNICAL DATA

(Statistical data obtained under standard conditions)

Aspect	WHITE powder
Water vapour permeability	$\leq \mu 15$
Adhesion	$\geq 0,3 \text{ N/mm}^2$
UNE-EN 998-1 Classification	GP CSIII W2
Approximate yield	16 Kg/m ² per cm of thickness

LEGAL DISCLAIMER

PRE-MIX PLASTERS AND MORTARS

MORCEMSEC® ENLUCIDO FINO CON CAL

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.