



PEGOLAND® DOS PORCELÁNICO

Cement-based adhesive with mixed binders



GlobalEPD
A VERIFIED ENVIRONMENTAL DECLARATION



DESCRIPTION

Cementitious adhesive made of mixed binders, non slip and extended open time. Suitable for interior and exterior pavements, interior claddings and baseboards. Suitable for the placing for all kind of ceramic pieces, porcelain clay, natural stone, granite and marble. High grip strength, good workability and aging resistance.

TECHNICAL CHARACTERISTICS

Highly resistant cement based product, select aggregate, additives and synthetic resins that guarantee a high grip strength, good workability and resistance to aging.

ADVANTAGES AND USES

- Excellent initial adherence.
- No need to wet tiles or substrates thanks to its high water-retaining capacity.
- Suitable for the placing for all kind of ceramic pieces, porcelain clay, natural stone, granite and marble.
- Suitable for interior and exterior pavements, interior claddings and baseboards.
- Swimming pool tiling.
- Suitable for the tiling of intense traffic areas.
- Suitable for tiles overlaying.

SUITABLE SUBSTRATES

- Conventional cement-based substrates.
- Suitable for adhesion on all types of plasterboard drywalls.
- Do not apply on gypsum or paint.
- Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products, etc.
- All substrates must have the appropriate flatness. Otherwise, smooth down up to 5 mm with the same product 48 hours prior to bonding. In case of greater thickness should be used:
 - On floors: Depending on the particular need use NIVELAND 10 R or PAVILAND RECRECIDO AUTONIVELANTE.
 - On walls: mortars with adequate tensile strength with drying shrinkage already completed.
- In case of hot or windy weather conditions or when applying over absorbent substrates, it is advisable to wet the substrate and wait till the thin layer of water disappears.
- On outdoor flooring, substrates must have a gradient equal or superior to 1%.
- Marble, granite, natural stones and all kind of ceramic pieces supports in interior pavements.



TILE AND STONE ADHESIVES

PEGOLAND® DOS PORCELÁNICO

APPLICATION PROCEDURE

- Add water and mix by hand or mechanically until an even and workable consistency is obtained.
- Let the mixture stand for 5 minutes and remix.
- Spread the mixed product on the substrate with a trowel to a maximum surface area of 2m².
- Spread with a notched trowel to adjust thickness (see chart).
- Place the pieces on the fresh adhesive, pressing and moving until the grooves are completely crushed and the entire surface of the ceramic is properly adhered, periodically check the stickiness of the adhesive by lifting a previously laid tile, if a non-transfer film appears on the surface of the adhesive, or dehydration of the adhesive, proceed to remove the material and apply a new product.
- Laying the tiles by a double glueing method outdoors, for formats greater than 900cm², on floors of commercial or industrial use, if there is underfloor heating, when laying ceramic sheets, if using levelling systems or if the tiles have a relief such as that good contact with the adhesive is difficult.
- Observe construction joints (expansion, contraction, fraction, perimeter corner joints) and the joints between the cement slabs (minimum 2mm).
- Joints should be grouted 24 hours after if on vertical surfaces, and 48 hours after if on floorings. Use the appropriate mortar from the MORCEMCOLOR range depending on the type of joint.

NOTE: For better results lay tiles as soon as possible after spreading.

NOTCHED-TROWEL PANEL

Maximum weight on vertical surfaces: 40 kg/m ²		
TILE FORMAT	NOTCHED TROWEL	BONDING
< 100 cm ²	U4 (4 x 4 x 4)	Simple
≤ 450 cm ²	U6 (6 x 6 x 6)	Simple
≤ 900 cm ²	U6 (6 x 6 x 6) / U9 (9 x 9 x 9) ó n10	Double-Simple
> 900 cm ²	U9 (9 x 9 x 9) ó n10	Double

RECOMMENDATIONS

- Do not apply below 5°C nor above 30°C.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- Do not use the technique known as by globs.
- Working and setting times of the adhesive depend on the temperature, air streams, and the absorption of tiles and substrates.
- Under extreme weather conditions (gusty winds or high temperatures) drying may occur faster.
- Tiled areas of walls and floors above 50 m² indoor and 30 m² outdoor or elongated more than 15 linear m it is recommended to divide them with joints filled with a deformable grout among PUMALASTIC range.
- In case of Indoor floor tiled it is recommended to leave a free perimeter joint between the tiles and the wall or pillar of about 5 mm hidden by the plinth. These joints must be filled with a deformable grout among PUMALASTIC range.
- On interior floorings larger than 15 m², it is advisable to keep a free perimeter expansion joint between the floor and the wall or pillar, hidden by a baseboard.
- When the application is taking place on plasterboards verify board is firmly fixed before applying on it.
- The swimming pool can be refilled after 7 days of applying the adhesive.
- The watertightness of the swimmingpool must be guaranteed by the underlying concrete structure.
- For gypsum based substrates, use PEGOLAND ESPECIAL YESO or PEGOLAND PORCELANICO YESO or PEGOLAND PROFESIONAL range, avoiding slaked or poor plaster.
- For slate use PEGOLAND FLEX RECORD and PEGOLAND PROFESIONAL FLEX ELITE.
- In case of tiles reinforced with fiberglass mesh on their back, please consult our technical department.
- When working with tiles that can be stained due to their high water absorption should be placed with PEGOLAND FAST FLEX C2FTE S1.
- On ceramic pavements (overlays), remove the badly adhered pieces and fill the gaps with mortar the day before the application of the new tiling. Ensure that the old ceramic is free of traces of fats or waxes, if necessary proceed to the milling of the enameled surface until the loss of brightness of the old ceramic. In case of doubt, make a preliminary test to establish the suitability of the solution provided.

TILE AND STONE ADHESIVES

PEGOLAND® DOS PORCELÁNICO

PACKAGING AND STORAGE

25 kg plastic-lined paper bags.
Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.

TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Aspect	WHITE or GREY powder
Adjustment time	Approx. 30 min. (depending on weather conditions)
Paste shelf life	Approx. 2 hours (depending on weather conditions)
Initial tensile adhesion strenght	$\geq 1 \text{ N/mm}^2$
Tensile adhesion strenght after water immersion	$\geq 1 \text{ N/mm}^2$
Tensile adhesion strenght after heat ageing	$\geq 1 \text{ N/mm}^2$
Tensile adhesion strenght after freeze-thaw cycles	$\geq 1 \text{ N/mm}^2$
Service temperature	from -30°C to 90°C
UNE-EN 12004 Classification	C2 TE
Approx. yield simple gluing	4 Kg/m ²
Approx. yield double gluing	6 Kg/m ²

ENVIRONMENTAL PRODUCT DECLARATION (EPD)

Cement based mortar prepared with aggregates that are supplied close to the production center, which reduces the greenhouse gas emissions that would otherwise arise from their transport. Manufactured in production centers with an Environmental management certified system following ISO 14001 regulation, offering a firm promise of sustainability and respect for the environment.
Cement based mortar with type III ecological label (the most strict) Environmental Product Declaration verified externally by AENOR.

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.