

PAVILAND® SPORT AC GRUESO

Aqueous acrylic resin with mineral load.

With approval from the International Tennis Federation (ITF).



DESCRIPTION

Acrylic resin base mortar for layers levelling of the surface in sports and pedestrian areas or in bicycle lanes. This pavement product is very easy to apply and it's suitable for the compensation of irregularities. It is a water base product suitable for indoor and outdoor floors. Also suitable for car park areas with little traffic. Black colour.

TECHNICAL CHARACTERISTICS

Aqueous acrylic resin with mineral load.

ADVANTAGES AND USES

- Easy to apply.
- Compensation of irregularities.
- Anti-slip.
- Water Base product, without solvents.
- Indoors and outdoors.
- Sports area pavements.
- Bicycle lane.
- Hard shoulders, islands, signs, side-walks, etc.
- Interior garages or outdoors car park areas with very little traffic.
- Especially indicated in the renovation of asphalt sports courts.

SUITABLE SUBSTRATES

- Concrete or asphalt of adequate resistance, open pore and slight roughness.
- Substrates must be resistant enough, stable, healthy and clean. Free of dust, release agents, organic products, etc.
- **Concrete substrate:** PAVILAND SPORT EPW PRIMER must be applied beforehand (consult the corresponding technical Data sheet for the evaluation of the concrete).
- **Asphalt substrate:** They must be resistant, stable, healthy and clean, free of dust, remains of release agents, organic products, etc. Properly repair the gaps and/or fissures that may be on the substrate using PAVILAND COLD ASPHALT. Before applying PAVILAND SPORT AC GRUESO the absorption of the substrate should be regularised using PAVILAND AC SELLADOR

APPLICATION PROCEDURE

- The product is ready to be used. Homogenise it with a suitable mixer, at low speed for two minutes before using it. It can be diluted in water up to 5% maximum.
- Pour the product on the substrate and spread it with a rubber trowel, starting from the corner and continuing linearly from end to end, paying special attention to singular points (encounters with vertical walls, etc.).
- The total thickness of product to be applied on one coat must not exceed 1.5 mm. Any superior thickness should be applied in various layers.

RECOMMENDATIONS

- Do not apply under 10°C.

FLOORING

PAVILAND® SPORT AC GRUESO

PACKAGING AND STORAGE

COLOUR RANGE

TECHNICAL DATA

- Do not apply above 30°C.
- Do not apply under risk of frost, rain, heavy wind or direct sun light.
- Use gloves and goggles when using it. In case of eye contact, clean with abundant water and soap and visit a specialist.
- In case of skin contact, clean the area with abundant water before it dries.
- Keep away from children.
- Tools should be clean immediately after being used with water. Once the product gets hard, it will only be removed by mechanical means.
- Do not eat or smoke while using the product.
- Empty containers should be thrown according to the current legislation.

22 kg containers

Store the product up to 1 year in its closed original package, in cool and dry places, away from direct sun light and between 10-30°C temperature.

Black

(Statistical results obtained under standard conditions).

Aspect	Black paste
Approximate density of the paste	1,7 Kg/dm ³
Resistance to Taber abrasion 8 days (CS10/1000 g/1000 cycles)	82 mg
Approximate performance	1 - 1,5 Kg/m ² /Layer

Application time

Initial curing	10-24h/temperature
Waiting time for pedestrian traffic	6-12h/temperature
Waiting time before the application of the intermediate layer or sealing of the system	6-12h/temperature
Time to dry touch	6-12h/temperature

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.