



MORCEM® COLOR ULTRA CG2 A W

High performance fast-setting and fast-hardening grouting mortar for joints from 2 to 20 mm.



DESCRIPTION

High performance coloured grouting mortar with additives and anti-fungi/anti-algae properties. Fast-setting and fast-hardening, anti-efflorescences and water repellent grout mortar with great plasticity for the sealing of joints from 2 to 20 mm. Highly recommended for areas where the applied product is required to be quickly ready to use and ready for traffic. All type of ceramic pieces grouting in intense traffic areas, swimming-pools, floors with radiant heating systems and for its application in areas prone to the growth of microorganism.

TECHNICAL CHARACTERISTICS

Product based on especial agglomerates (it does not contain portland cement), high purity aggregates, pigments and special additives.

ADVANTAGES AND USES

- Grouting mortar for pavements and claddings; for interior and exterior areas; suitable for all type of ceramics, porcelain clay tiles, marble, granite, vitreous mosaic and natural stone.
- Highly recommended for areas where the applied product is required to be quickly ready to use and ready for traffic. Suitable for intense traffic and residential areas, swimming-pools, façades, balconies, terraces and radiant heating floors.
- Aquastop effect: It repels superficial water from the joints producing a pearl effect, the surface, with a very low porosity and minimum water absorption, makes the joint very easy to clean.
- Bioactive technology: Avoids micro-organisms proliferation (fungi and algae) in humid environments.
- Fast and easy to clean during its application with an optimum and fast finish.
- Resistant to cracking and fissures due to its low retraction and great durability against abrasion and mechanic resistance even during frosting/defrosting processes.
- Uniform colours, thanks to its saline efflorescences blocking technology. It does not contain any Portland cements and therefore when it comes to the moisturising of the product, it does not produce any calcium hydroxide which leads to efflorescences, avoiding this unwanted effect in the colour and finish of the joint.
- Colours resistant to UV rays and exterior exposure.
- Good resistance against oils, solvents, alkalis and pH>3 acids.

SUITABLE SUBSTRATES

- Before applying the grouting, make sure the adhesive is completely hard, taking into account that given timings in the data sheet have passed.
- Empty joints must be dry and clean, without dust or any other adhesive rest; they should have a uniform depth, 2/3 minimum from the total thickness.
- Some ceramic tiles may show signs of micro-porous or roughness in the surface area. It is advisable to carry out a preliminary test in order to verify that it can be cleaned and, when necessary, apply PROTECMOR (temporary pore sealer), on top of the surface avoiding any possible stains of pigment from penetrating the porosity of the surface in the tiles.

TILE GROUTS

MORCEM®COLOR ULTRA CG2 A W

APPLICATION PROCEDURE

- Add water (23%- 27%) and mix it manually or mechanically with a spiral mixer at low revs (400 rev/min aprox.) until getting a consistent paste (not a liquid one), homogeneous and without lumps. Let the mixture rest for 2 minutes and mix again.
- As we are working with a fast drying grouting we should take into account that the amount mixed should be the adequate to be used within 20-25 minutes.
- Fill the joints using a rubber trowel and firmly compact the material without leaving any gaps, remove any excess of paste while it remains fresh, using the rubber trowel in a diagonal sense from the joints and removing the excess of material.
- Let the material dry for approximately 15 to 30 minutes, once the paste has turned matte, you may clean the surface with a hard sponge of great dimensions in order to avoid the damage of the joints, make sure it is slightly moisten, use rotating movements in order to remove the excess of hardened grouting and finish going over the joints with diagonal movements, often clean the sponge with clean water and always use a uniform quantity of water in order to avoid colour changes.
- Just once the product is hard enough in the joints, we will be able to proceed with the polishing of the surface with a clean and dry cloth to clean the dust (try to avoid cleaning before time, because if the grouting is still wet, it might have effects and produce changes in the colour).
- If the tiles were dirty or had lumps after cleaning them, you may use DESMOR cement remover (check instructions in its technical data sheet) in order to clean it, always use it on acid resistant tiles and make sure not to touch the joints. Rinse the tiles with clean water to eliminate any possible remains of acids.
- Grouted areas can be transited three hours after the product has been applied, wait for 24 hours before putting it into service and 48 hours in tanks and swimming pools.

RECOMMENDATIONS

- Do not apply it under 5°C or above 30°C.
- Do not apply it under freezing, rain, heavy winds or direct sun weather conditions.
- Do not add water in excess, as it may reduce its final output.
- Do not apply it on substrates that may suffer from rising damp.
- Fill the joints once the pavement or the cladding is completely dried.
- In case of very absorbent tiles or extremely high temperatures, before filling the joints, moisten them with clean water, using a humid sponge avoiding any excess of water.
- Do not clean the joints with nitric acid or other kind of acids as it will affect the colour.
- In tanks and pools wait at least 48 hours after the grouting has been applied before filling them.
- MORCEMCOLOR ULTRA does not contain Portland cement and it should not be mixed with plaster or any other hydraulic agglomerates; never mix with salty or dirty water and never add water to a mixture that has already started its hardening process.
- When acid resistance or high hygiene is required we suggest using MORCEMCOLOR EPOXI.
- Do not use it with dilatation or division joints or joints which are held to structural movements during the work process, these joints must be refilled with a deformable material from the PUMALASTIC range.
- Working times of the joint may prolong or reduce according to the environmental temperature and the water temperature of the mixing.
- Do not clean with an excessive amount of water, or while the product is still fresh, to avoid carbonation and discolouration of the surface due to pigment dispersion.

TILE GROUTS

MORCEM®COLOR ULTRA CG2 A W

CONSUMPTION ACCORDING TO DIMENSIONS (KG/M²)

Valid values for 6mm thickness pieces.

TILE FORMAT	JOINT WIDTH				
	2 mm	5 mm	10 mm	15 mm	20 mm
2 x 2 cm	1,3 (Calculation done for a separation between tiles of 4 mm)				
15 x 15 cm	0,27	0,68	1,36	2,04	2,72
15 x 20 cm	0,24	0,60	1,19	1,79	2,40
20 x 20 cm	0,20	0,51	1,02	1,63	2,05
25 x 33 cm	0,14	0,36	0,72	1,08	1,45
30 x 40 cm	0,12	0,30	0,60	0,89	1,20
40 x 60 cm	0,09	0,21	0,43	0,64	0,85
45 x 80 cm	0,07	0,18	0,35	0,53	0,70

$$((A+B)/A \times B) \times C \times D \times 0,17 = \text{Kg/m}^2$$

Where:

A= width of the tile (cm)

B= length of the tile (cm)

C= thickness of the (cm)

D= width of the joint (cm)

PACKAGING AND STORAGE

5 Kg polyethylene bags.

Shelf life: 2 years (5 Kg polyethylene bags) in its sealed original packaging, sheltered from weather conditions and humidity.

TECHNICAL DATA

(Statistic results obtained under standard conditions, at +23°C and 50% H.R)

Classification according to UNE-EN 13888-1	CG2 F W A
Classification according to ISO 13007-3	CG2 F W A
APPLICATION DATA AND ASPECT	
Aspect	White and colour range
Application temperature	+5°C a +30°C
Mix duration	20 - 25 min
Waiting time for its finishing	15 - 30 min
Trafficability	Aprox .3 hours
Put into service	24 hours (48 hours in tanks and pools)
OUTPUT	
Compression resistance after 24 hours	>15 N/mm² (EN 12808-3)
Flexural resistance after 28 days	>5 N/mm² (EN 12808-3)
Compression resistance after 28 days	>30 N/mm² (EN 12808-3)
Flexural resistances after frost/thaw cycles	>5 N/mm² (EN 12808-3)
Compression resistance after frost/ thaw cycles	>30 N/mm² (EN 12808-3)
Retraction	<1,5 mm/m (EN 12808-3)
Abrasion	<700 mm³ (EN 12808-2)
Water absorption after 30 minutes	<0,2 g (EN 12808-5)
Water absorption after 240 minutes	<0,5 g (EN 12808-5)
Service temperature	-20°C a +80°C
Resistance to acids	Good (si pH>3)
Resistance to alkalis	Optimum

TILE GROUTS

MORCEM®COLOR ULTRA CG2 A W

LEGAL DISCLAIMER

Resistance to oils and solvents

Optimum

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.