

UNOFIN ANCILLARY PRIMER

Mortar bonding bridge



DESCRIPTION

Adherence primer to promote cement, lime-based mortars and/or plaster-based renders' anchorage on smooth concrete or substrates lacking superficial absorption.

TECHNICAL CHARACTERISTICS

Product containing synthetic resins, mineral fillers and organic and inorganic additives.

ADVANTAGES AND USES

- For indoor and outdoor application.
- Apply on vertical faces and ceilings.

APPLICATION PROCEDURE

- Mix 2 parts UNOFIN ANCILLARY PRIMER with 1 part water.
- Apply the mixture with paint roller or large paintbrush.
- Once dry, apply the mortar.

NOTE: Do not apply the mortar more than three days after applying UNOFIN ANCILLARY PRIMER.

RECOMMENDATIONS

- Substrates must be clean, dust free, grease, oil, liquid, demolding agents, etc.
- Do not apply when there is a risk of rain or frost.
- Clean the used tools with water right after its use.
- Do not apply the one-coat mortar if UNOFIN ANCILLARY PRIMER is still wet.
- Pay special attention in the application of cement-lime mortars made on site, due to the non-uniform tensions that they can cause. In these cases use a latex, to soften these tensions.
- Do not apply on humid supports.
- Do not apply on gypsum supports.
- Do not apply with temperatures lower than 5°C or higher than 30°C.

PACKAGING AND STORAGE

20 kg buckets.

Shelf live: 1 year in sealed original packaging.

TECHNICAL DATA

(Statistical results obtained under standard conditions)

Aspect	Yellow paste
Density	1.65 g / cm ³
Viscosity	300 ± 100 dPas
Solubility	Freely soluble in water
Fire behaviour	Non-flammable
Yield	0.3 Kg/m ²

UNOFIN ANCILLARY

UNOFIN ANCILLARY PRIMER

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by PIDILITE GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

PIDILITE GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of PIDILITE GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by PIDILITE GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.