



NIVELAND® 10 CT C25 F5

Self-levelling mortar suitable for 2 to 10 mm thickness



DESCRIPTION

Self-levelling mortar for interior residential floors that once harden accepts any kind of pavements: ceramic, parquet, etc. 2mm to 10 mm thickness. Mortar for levelling irregular pavements indoors. High mechanical resistance. Easy to lay and high self-levelling power.

TECHNICAL CHARACTERISTICS

Product based on cements, selected aggregates and additives.

ADVANTAGES AND USES

- Irregular pavements levelling in interior areas.
- High mechanical resistance.
- Easy to apply
- High self-levelling capacity.
- Floors' smoothing in residential areas with moderate pedestrian traffic, before placing the final pavement: ceramic, parquet, PVC, linoleum, etc.

SUITABLE SUBSTRATES

- Concrete, cementitious floorings or substrates with a suitable resistance or similar strength. In case of working with other substrates, please consult our technical department.
- Substrates must be resistant, stable, sound, and clean, free from dust or any other kind of substances, organic products, etc.
- If necessary prepare the substrate mechanically so that the surface is free from grout and has the appropriate porosity.
- Before applying NIVELAND 10, any possible hollows and cracks should be adequately repaired using the PAVILAND or MORCEMREST adequate product, according to the nature of the substrate and the type of reparation required.
- Apply Paviland Primer R to avoid the formation of air bubbles in the cladding and in order to improve its adherence to the substrate according to the instructions given in the technical data sheet of the product.
- Before applying the paste, ensure that the residual humidity is below the recommended level (lower than 3%).

APPLICATION PROCEDURE

- Mix the product with water (5.00-5.25 L per each 25 Kg bag), with a mechanic mixer at low speed (500 rpm approximately) until getting a homogeneous paste without lumps. It is essential to add the exact specified amount of water in order to avoid the segregation of the product, high retractions and a decrease in resistance.
- Let the mixture stand for 2 minutes and remix.
- The paste should be used during the following 30 minutes after it has been prepared, this, of course, will depend on environmental conditions as well.
- Pour the mixed product on top of the substrate and spread it with a levelling trowel.
- The maximum thickness suggested would be around 10mm thickness applying it in just one layer.
- Respect the structural joints and carry out perimeter and partition joints.

FLOORING

NIVELAND® 10 CT C25 F5

RECOMMENDATIONS

- NIVELAND 10 must be protected, as it is not an appropriate material to remain uncovered.
- Do not apply it under 5°C nor above 30°C.
- Do not apply when there is a risk of frost, strong wind or direct sun weather conditions
- Not recommended for exterior use Do not apply on floors with humidity or that may suffer from it in the future.
- Do not add any aggregates, cement nor any type of product that may modify the original formula.
- Once the product has been mixed and its resting time has passed, do not add any more water.
- For floors larger than 20 m² or longer than 10 lineal metres, it is advisable to make partitioning joints, delimiting panels with 6 mm joints that can be sealed with PUMALASTIC MS or PU.
- Movement joints on the original substrate must be respected and perimetric joints made.
- The surface coat should be protected against an extremely fast drying, specially under high temperatures or heavy winds conditions.
- Before placing the final pavement, you should check the residual humidity of the floor and confirm it is adequate for the type of flooring to be installed.

PACKAGING AND STORAGE

25kg laminated paper bags.

1 year storage in its original packaging, away from extreme weather conditions and humidity.

TECHNICAL DATA

(Statistic results were obtained under standard conditions).

Aspect	Grey powder
Life time of the paste	30 minutes
Adherence to concrete	>1 N/mm ²
Time to wait before walking on surface (*)	8– 12 hours
Sanding time (*)	12– 24 hours
Cladding time (*)	Ceramic or carpet: 12-24 hours
	Parquet or synthetic cladding: 24-48 hours
compression strength	> 5 N/mm ² (1 d)
	> 15 N/mm ² (7 d)
	> 25 N/mm ² (28 d)
Approximate yield	1,5 Kg/m ² and mm thickness
Classification according to UNE EN 13813	CT C25 F5
Thickness of application:	2 a 10 mm

(*): Time refers to a temperature range around 23°C and 55% relative humidity. They are shorter at higher temperatures and longer at lower temperatures.

FLOORING

NIVELAND® 10 CT C25 F5

CE MARK

	
GRUPO PUMA SL	
Avda. AGRUPACIÓN CÓRDOBA, 17 14014 CÓRDOBA 18 Nº:501870-01	
EN 13813	
NIVELAND 10	
Self-levelling mortar (CT.C25-F5 type) for indoor floors preparation, installation of light floorings such as tiles, parquet, fitted carpet, etc. Thickness from 2 mm to 10 mm.	
Fire reaction	Clase A1
Emission of harmful substances	CT
Compressive Strength	C25
Flexural Strength	F6
Dangerous substances	Check Safety Data sheet

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.