



ADHESIVO CARBOTEC LÁMINA

DESCRIPTION

Adhesivo Carbotec Lámina is an epoxy resin. Bi-component resin and free from solvents. It has great adhesion to all types of substrates, even without primer and high resistance to abrasion.

ADVANTAGES AND USES

- As an adhesive for carbon fiber sheets for structural reinforcement.
- As an adhesive for steel plate.
- Excelent adhesion: exceeds the coherence to the substrate.
- Fast curing.
- Filling of fissures / stable cracks/ without movement.
- Leveling of surface defects such as honeycombs, hollows, etc.
- For shaping lips of concrete or metal joints without movement,
- Renovation of edges, mortars and concrete.
- Adhesive for elastic PVS membrane,
- High resistance to abrasion and impact.
- Curing without retraction.
- High resistance
- Easy to mix and apply.

SUITABLE SUBSTRATES

- The surface to be treated must be clean, degreased and free from dust in order to obtain an adequate adhesion.
- On steel surfaces remove surface rust.
- It is recommended the pore of the concrete to be open or create a slight surface roughness to ensure adhesion.
- It is recommended to apply Implarex EPW when the quality of the concrete is insufficient.

CONCRETE REPAIR

ADHESIVO CARBOTEC LÁMINA

APPLICATION PROCEDURE

- Stir each component before mixing in order to eliminate grounds.
- Add component B in its totality to component A. This ensures that the volumetric ratio between component A and component B is correct.
- Mix in a low velocity electric mixer (less than 300 rpm) for about 3 minutes, until getting a homogeneous gray mixture.
- Avoid air bubbles.
- Apply Adhesivo Carbotech Lámina with spatula.
- The surface must be clean, dry and free from dust before applying Adhesivo Carbotech Lámina.
- It is preferred to apply the adhesive to the Carbotech carbon fiber sheet or steel plate.
- Apply the adhesive in such a way that it is not flat and uniform, but thicker in the center (approx. 5mm) and progressively thinner at the ends (approx. 1 mm).
- Press the Carbotech carbon fiber sheet or steel plate uniformly over the concrete to spread the adhesive. It is recommended to press with a hard rubber roller, which also removes air bubbles. Clean the excess adhesive before it hardens.
- Keep the pressure on the carbon fiber until the adhesive has hardened sufficiently.
- The final thickness of the adhesive coat is 1.5 mm to 2 mm.

RECOMMENDATIONS

- Mixing and application equipment should be cleaned with solvent.
- Remove hardened material by mechanical means.
- Consult our Technical Department for any application that might not be specified in this Technical data sheet.
- For additional information regarding the safe handling, transport, storage and use of the product, please refer to the label and the updated version of the product Safety data sheet.

CONSUMPTION ACCORDING TO DIMENSIONS (KG/M²)

Consult Lámina Carbotech technical data sheet.

PACKAGING AND STORAGE

5 kg containers.

Keep it in its original packaging in a dry place with temperatures that may go from 5°C to 30°C. Once the container is opened, its service life is considerably reduced, so it should be used as soon as possible. Rotate the stored product so that it does not exceed the expiration date (1 year).

TECHNICAL DATA

Properties	Value
Colour	Gray
Specific weight	1.7 gr/cm ³
Solid content	>99%
Viscosity	>12.000 cps
Post – life 25°C	30 min 20°C
Dry to touch	3 hours
Minimum operating temperature	5°C
Walkable at foot	3 hours
Time between coats	3h. minimum– 24h. maximum
Average consumption	According to tables
Adhesion to concrete	>3 N/mm ² (> own cohesion)
Adhesion to steel	>15 N/mm ²
Tensile elongation at break	≥ 1%
Compressive strength	>150 N/mm ²
Tensile strength	>65 N/mm ²

CONCRETE REPAIR

ADHESIVO CARBOTECH LÁMINA

CE MARK

Resistance to freeze-thaw cycles	Excellent
Glass transition temperature (Tg)	+ 60 ° C

(*)Typical values after curing for 7 days under a conditioned temperatura of 21°C. Mechanical properties decrease at temperaturas above 50°C.

CE GRUPO PUMA SL Avda. Agrupación Córdoba 17 ,14014 Córdoba 21 Nº: 260011 ADHESIVO LÁMINA CARBOTECH			
Key characteristics	Features	Harmonized technical specification	Harmonized Standard
Lifetime variation in adhesion	3.6 Mpa (initial) 3.5 Mpa (15 min) 3.5 Mpa (30 min)	UNE-EN ISO 9514/1542	
Adhesion to steel/tensile strength	≥ 14 N/mm ²	UNE-EN 12188:2000	
Adhesion to steel/Shear resistance	≥ 50 N/mm ² (50°C) ≥ 60 N/mm ² (60°C) ≥ 70 N/mm ² (70°C)	UNE-EN 12188:2000	1504-4:2005
Modulus of elasticity in compression	> 2000N/mm ²	UNE-EN 13412:2008	
Glass transition temperatura (Tg)	≥ 40 °C	UNE-EN 12614-1:2004	
Linear shrinkage	≤ 0.1%	UNE-EN 12617-1:2004	
Coefficient of thermal expansion	≤ 100 µm/m°C	UNE EN 1770:1999	

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively

CONCRETE REPAIR

ADHESIVO CARBOTEC LÁMINA

to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.

Rev. 24_10 · This revision cancels all previous ones. Please, obtain the latest version from our web site · www.grupopuma.com · (+34) 957 76 40 40