

FONDO MORCEMCRIL SILICATO

Base paint for silicate mortar



DESCRIPTION

Sealer based on high-quality silicate emulsion, suitable as base for the subsequent application of Morcemcril Silicato. It Improves adhesion, it makes the application easier, homogenizes the absorption of the substrate and gives an initial coloured coverage.

It favours the coverage and performance of the finish acrylic mortar, maintaining high permeability to water vapour. Excellent application, workability, and adhesion to the substrate.

ADVANTAGES AND USES

- Good coverage.
- Impervious to rainwater and permeable to air and water vapour.
- Good resistance to the substrate's alkali.
- Good homogenisation of the product and easy to apply.
- Substrates must be clean, dry, and free from greases, without cracks or detached materials.
- Apply diluted Fijador-Sellador in 3 parts of water in case of non-unified or very porous substrates.
- Apply the paint according to the instructions given.

APPLICATION PROCEDURE

- Stir the content until perfect homogenisation.
- You may dilute approximately 10% in water depending on work conditions and parameters to be sealed.
- It can be applied by brush, roll or pistole, previously shaking and diluting the product, respectively.
- Tools must be cleaned with abundant water before the paint dries.

RECOMMENDATIONS

- Do not apply under 5°C.nor above 35°C.
- Do not apply the product with relative humidity above the 85% nor on wet substrates. Fog or high ambient humidity can delay the final hardening of this material)
- Keep in fresh and dry places.
- Due to its strong alkaline character, it is recommended to use protective equipment when managing this highly alkaline product.
- It is advisable to wear gloves and protective goggles. In case of direct contact with the eyes, rinse thoroughly with abundant water.
- Cover wooden or aluminium frames.

PACKAGING AND STORAGE

12 litres packaging.

Preservation: Store up to 12 months in its original closed container, away from extreme weather conditions.

DECORATIVE PLASTERS

FONDO MORCEMCRIL SILICATO

TECHNICAL DATA

Alloy	Acrylic/Silicate
Solvent	Water
Specific weight	1,43 +/- 0,03 Kg/l
Viscosity 22°C	90 dPas +/- 10
pH	11.5
Theoretical performance	8 to 10 m ² /litre
Drying time	To touch: 1 hour total: 2 hours
Finish	matte

Timings are given according to temperatures of 23°C and 55% relative humidity. Periods of time will be shorter at higher temperatures and longer at lower temperatures.

LEGAL DISCLAIMER

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMA's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.