

PUMAFLEX PU HYBRID



DESCRIPTION

Weatherproof water based polyurethane membrane.

Coating for horizontal substrates based on acrylic polymers and aliphatic polyurethane. It forms a continuous and elastic high-performance coat capable of preventing water infiltration and the resulting moisture-related issues.

Especially suitable for preventing water infiltration on terraces, rooftops, roofs, partition walls, expansion joints, channels, downspouts, etc. It can be applied to any exterior surface that is occasionally walkable, provided it is not subjected to daily or intensive traffic.

ADVANTAGES AND USES

- Rainproof.
- Good tensile strength and high elasticity.
- Greater mechanical strength with the use of fibreglass mesh.
- Good homogenisation of the product and easy to apply.
- Notable resistance to abrasion.
- Good crack filling capability and resistance to microcracking
- Due to its UV radiation crosslinking, it has excellent dirt resistance.
- Very low residual tackiness of the dry film.
- Resistant to open air and ultraviolet rays.
- High Solar Reflectance Index (SRI) in its white version, reducing heat absorption.
- It can be applied using a brush, roller, airless spray gun or pistole. Make sure the product has been previously mixed and correctly diluted.
- Tools must be cleaned with abundant water before the paint dries.

Not suitable for permanent water contact, water storage, ponding, or significant condensation.

Examples: swimming pools, tanks, ponds, cisterns, planters, etc.

SUITABLE SUBSTRATES

NEW CONSTRUCTIONS:

- Concrete, cement, plaster, brick, stone, fibre cement, etc., must be cured, dry, firm, and free of dirt or grease.
- Treat efflorescence or salt deposits with diluted DESMOR, rinse, and allow to dry.
- Surfaces must be free of moss and microorganisms and should be dry or only slightly damp.
- In the case of cracks, holes, or flaking, repair them before applying the product.
- Apply the paint according to the instructions given.

OLD CONSTRUCTIONS:

- Treat efflorescence or salt deposits with diluted DESMOR, rinse, and allow to dry.
- Remove any mould contamination using bleach or any other suitable product as well as any remaining paint or other construction materials.
- On deteriorated substrates, those with poor cohesion, or moisture issues, apply FIJAMOR beforehand.
- In the case of cracks, holes, or flaking, repair them before applying the product.
- Remove sharp or cutting elements, such as damaged tiles, which could mechanically damage the membrane and replace any defective pieces.

ACRYLIC RUBBER

PUMAFLEX PU HYBRID

APPLICATION PROCEDURE

- The old coating should be brushed to remove loose particles, then cleaned and degreased.
- Apply PUMAFLEX PU HYBRID according to the instructions given.
- Shake until perfect homogenisation.
- Dilute the primer coat by a 15% with water and spread it. Ensure thorough wetting of the entire surface, especially around the perimeter and in cracked areas.
- Apply the second and subsequent coats undiluted, in the opposite direction of the previous one. A minimum of two coats must be applied, ensuring that the previous one is completely dry before proceeding.
- On frequently walked surfaces, a fibreglass or polyester fabric reinforcement should be placed over the first undiluted coat. – The successive sections of this reinforcement must overlap by 10 cm, ensuring that the topcoat aligns with the slope direction of the floor. The reinforcement must be stretched without wrinkles and then covered with additional coats of the waterproofing product.
- It can be applied by brush, roll or pistole, previously shaking and diluting the product, respectively.
- Tools must be cleaned with abundant water before the paint dries.

RECOMMENDATIONS

- If sealants or asphalts are present in the expansion joints, it is recommended to properly "bridge" them with an elastic polyester reinforcement.
- Whenever necessary, correct the slopes to prevent water ponding.
- At junctions with vertical surfaces, reinforcement with fibreglass or another suitable material is required, applying the product up to a height of 15 cm.
- Do not apply under 5°C.
- Do not apply the product with relative humidity above the 85% nor on wet substrates.
- Do not apply under the risk of rains.
- Keep in fresh and dry places.

PACKAGING AND STORAGE

4 and 15 litres containers.

TECHNICAL DATA

Aspect of dry film	According to Standard	Value
Colour	-	Blanco (White)
Finish	UNE - EN 1062-1	Semi-gloss matte
Shine 85°	UNE-EN ISO 2813	6.2
Chromatic coordinate L*	UNE 48073	92.24
Chromatic coordinate C*	UNE 48073	2.28
Chromatic coordinate H*	UNE 48073	92.24
Berger Whiteness	UNE 48073	75.71
Opacity	UNE-EN 13300	<95%
Residual Tac (g/ CM 2)	-	Initial= 0.
		After 4hr.U.V.=0

Physical properties	According to standard	Value
Density	UNE-EN ISO 2811-1	1.30 kg/L

ACRYLIC RUBBER

PUMAFLEX PU HYBRID

PH	INTERNAL	8.7
Viscosity	UNE-EN ISO 2555	100 dPas (50 rpm; Spindle R6)
Dispersion fineness	UNE-EN ISO 1524	20 Microns

Refer to its formulation	According to standard	Value
Non-volatile matter content	UNE-EN ISO 3251	59%
Maximum content in COV allowed	2004/42/II A classification	40 g/L
Maximum content in COV of the product	2004/42/II A classification	40 g/L

Properties of application	According to standard	Value
Theoretical performance	UNE 48282	1-1.5 m ² /l
Drying time to touch	UNE 48301	2 - 3 hours
Total drying time	UNE 48301	< 24 hours
Solvent	-	Water
1St hand dilution	As primer	15%
2nd and successive hands dilution	-	Without diluting
Repaint interval	Under average temperature	> 12 hours

Some other specific properties	According to standard	Value
Wet rub resistance	UNE-EN ISO 11998	Type 1

ACRYLIC RUBBER

PUMAFLEX PU HYBRID

Elongation	-	> 350 %
Resistance to traction	UNE-EN ISO 4624	2,5 N/nm ²

LEGAL DISCLAIMER

Instructions given on how to use the product are given based on our tests and knowledge and do not imply any commitment from GRUPO PUMA and do not exempt the user from checking and verifying the products before using them. Claims must be presented with the original packaging to allow an adequate traceability.

GRUPO PUMA is not responsible, under any circumstances, for the application of its products or constructive solutions by the applicator company or other subjects involved in the application and / or execution of the work in question, limiting the responsibility of GRUPO PUMA exclusively to possible damages attributable directly and exclusively to the products supplied, individual or integrated into systems, due to failures in their manufacture.

In any case, the creator of the work project, the technical management or person in charge, or subsidiarity the application company or other possible people involved in the application and / or execution of the work in question, must ensure the suitability of the products. Taking always into account the substrates and any possible pathologies that may occur in the workplace itself.

The values of the products or constructive solutions from GRUPO PUMA that are determined in the UNE standard, or any other applicable standard refer exclusively to the conditions expressly stipulated in that regulation.