

MORCEMCRIL® ULTRA FINO

DESCRIPTION

Acrylic coating for thin-coat application, ready-to-use product for waterproofing, protecting, and decorating all types of façades and interiors. Decorative coating mortar for the Traditem External Thermal Insulation system (ETICS).

TECHNICAL CHARACTERISTICS

Product based on acrylic resin, mineral pigments, and organic and inorganic additives.

ADVANTAGES AND USES

- Anti-mould.
- Rainproof.
- Permeable to water vapour, allowing the substrate to breathe.
- Non-flammable.
- Easy and quick to apply.
- Smooth finish.
- Suitable for the vast majority of substrates.
- Ageing, open environments and UV rays resistant.
- Excellent adhesion on traditional construction substrates.
- Washable.

This product has a protection against fungus, mould and algae which provides a long-lasting preventive and retardant effect although not permanent. The duration of this affectation depends on the exposure to humidity and the concentration of spores in the area, which create especially favourable conditions for the growth of micro-organisms. Therefore, periodic preventive maintenance treatment is recommended.

SUITABLE SUBSTRATES

- Compatible with cement mortar substrates, concrete, one-coat mortar, gypsum, plasterboard, and painted substrates.
- Not compatible with fresh lime plasters, resins or varnishes, distemper paints, lime, or silicate paints.
- Traditem external thermal insulation system prepared for the execution of the final decorative finish.
- Substrates must be clean, free from dust, greases, old paint, oils, fungus, mould, and any other kind of product.
- On surfaces with loose particles, apply FIJAMOR primer beforehand.
- Apply a FONDO MORCEMCRIL coat before applying MORCEMCRIL.

APPLICATION PROCEDURE

- Shake until getting a perfect mixture.
- The product is already ready to use, and it should be applied with a stainless-steel trowel.
- First coat: Apply the product using a stainless-steel trowel over the entire surface, with an approximate thickness of 0.5 mm, ensuring the surface is as uniform as possible.
- Once applied and the stickiness has diminished, any small imperfections should be evened out using a slightly damp sponge or a slightly damp sponge roller.
- Second coat: Repeat the same procedure as with the first coat. The total thickness of both coats should be approximately 1 mm to ensure the required protection of the system.
- It is recommended to work uniformly and without interruption in small areas (up to 2 m² per worker) due to the complexity of the application. The surface size will depend on the number of skilled workers and each worker's capacity. For larger areas, it is advisable to create working joints.
- The choice of tool affects the texture of the surface, so the same type should always be used on a construction site. To obtain a uniform structure, it is crucial to make sure that adjacent surfaces are structured by the same person.
- Due to the natural aggregates and granules in the product, slight colour variations between different batches may occur. Adjacent surfaces should use product from the same batch to ensure consistency.
- Cleaning of the tools will be conducted with abundant water immediately after being used. Any dried particles should be removed with solvents such as turpentine.

DECORATIVE PLASTERS

MORCEMCRIL® ULTRA FINO

RECOMMENDATIONS

- The maximum permissible thickness for this product is 1.5 mm, applied in 0.5 mm coats. Any thickness exceeding the specified coat or total thickness may cause cracking.
- Do not apply under 5°C nor above 30°C, under direct sun light, rain, or heating risk.
- Do not apply on floors or on slopes of less than 45°.
- Do not apply in thicknesses greater than 0.5 mm (1.5 mm maximum in three coats).
- Flatness criteria for the substrate are stricter than for standard finishes in order to achieve an optimal result, so it is highly recommended to apply the base coat in three hands, giving priority to fine flatness in the final one.
- The smooth finish of Morcemcrl Ultra Fino enhances the water ripple effect on surfaces when exposed to raking light—this is a normal occurrence in manually applied systems, and all construction stakeholders should be informed. A sample working area is recommended for approval.
- Protect the upper surfaces of the render from the penetration of rainwater.
- Pay special attention to environmental temperature changes, humidity, wind, etc. These factors influence the drying process and the workability of the product, potentially causing differences in the final appearance of the application.
- Protect the surrounding area of the surface to be applied and clean any possible splashes with water before the product dries or hardens.

PACKAGING AND STORAGE

20 Kg containers

Storage: Storage Up to two years in its original closed packaging. In fresh and dry places, away from open air and direct sun light. Avoid extreme weather conditions (not lower to 5°C nor above 35°C).

TECHNICAL DATA

DRY FILM ASPECT	VALUE	ACCORDING TO NORM
Colour	White	-
Finish	Matte	UNE-EN 1062-1

PHYSICAL PROPERTIES	VALUE	ACCORDING TO NORM
Density	1,78 Kg/l	UNE-EN ISO 2811-1
pH	8,6	Internal
Viscosidad	350 dPas (50 rpm; Husillo R7)	UNE-EN IS 2555

PROPERTIES OF APPLICATION	VALUE	ACCORDING TO NORM
Theoretical performance	1.8- 2.2 kg/m ² for 1 mm thickness	UNE 48282
Drying time to touch	30 minutes	UNE 48301
Total drying time	2 hours	UNE 48301
Solvent	Water	-
1 st hand dilution	10%	-
2 nd and successive hands dilution	5-10%	-
Repaint interval	3 - 4 HORAS	-

DECORATIVE PLASTERS

MORCEMCRIL® ULTRA FINO

LEGAL DISCLAIMER

OTHER SPECIFIC PROPERTIES	VALUE	ACCORDING TO NORM
ADHESION	> 15 kg/cm ² on concrete	EN 1542
Water absorption	Low (W3)	EN 1062-3
Permeability to water vapour	Sd 0.14- 1.4	EN ISO 7783
Thermal conductivity	0.83- 0.93 w/mK	EN 1745
Fire reaction	A2-S1 d0	EN 13501

The instructions for use are given according to our tests and knowledge and do not imply any commitment by GRUPO PUMA nor free the consumer from the examination and verification of the products for their correct use. Claims must be accompanied by the original packaging to allow a proper traceability.

GRUPO PUMA is not responsible, in any case, for the application of its products or constructive solutions carried out by the application company or other parties involved in the process and / or execution of the work, limiting the responsibility of GRUPO PUMA exclusively to the damages directly attributable to the supplied products, individually or integrated in systems, due to failures in their manufacturing process.

In any case, the drafter of the work project, the technical management or the person responsible for the work, or collaterally the application company or other parties involved in the process and / or execution of the work, must ensure the suitability of the products addressing the characteristics of them, as well as the conditions, support and possible pathologies of the work in question.

The values obtained by GRUPO PUMAS's products or its constructive solutions that, as the case may be, are determined by the EN standards or any other regulation that applies to it in each case refers exclusively to the conditions specifically stipulated in said regulation and that are referred to, among others, to certain characteristics of the support, humidity and temperature conditions, etc. without being them required in the tests obtained under different conditions, all in accordance with the relevant regulation.